



Technical Data Sheet

Product Name
SCGC™ HDPE

Product Type
High Density Polyethylene

Product Grade
F15

Product Description

F15 is a high density polyethylene product of bi-modal process. It is recommended for film which is produced by high speed machine and wide lay flat. The key characteristics are high tensile strength and high productivity.

Typical Application

- Shopping bags and T-shirt bags
- Garbage bags
- Liner bags

Product Characteristics

- High productivity
- High tensile strength with good dart
Impact strength
- Low gel content
- Excellent printing
- Good moisture barrier

International Compliance

- U.S FDA 21 CFR 177.1520
- Regulation (EU) No.10/2011
- Packaging and Packaging waste
Directive 94/62/EC
- RoHS Directive 2011/65/EU (RoHS 2)
- REACH Regulation (EC) No.1907/2006

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 190 °C, 2.16 kg	0.06	g/ 10 min
Density	ASTM D 1505 (anneal @ 100 °C)	0.952	g/cm ³
Melting Point	ASTM D 2117	130	°C
Vicat Softening Point	ASTM D 1525	123	°C
Brittleness Temperature	ASTM D 746	<-60	°C
ESCR	ASTM D 1693 (Method B, Compression Molded, 25% Igepal, 50 °C)	>1000	Hours, F ₅₀
Film Properties			
Tensile Strength at Yield	ASTM D 882	MD : -*-, TD: 320*	kg/cm ²
Tensile Strength at Break	ASTM D 882	MD : 910*, TD: 380*	kg/cm ²
Tensile Modulus, 2% Secant	ASTM D 882	MD : 11,000*, TD: 10,000*	kg/cm ²
Elongation at Break	ASTM D 882	MD : 350*, TD: 530*	%
Elmendorf Tear Strength	ASTM D 1922	MD : 6*, TD : 45*	g
Dart Impact Strength	ASTM D 1709	160*	g

- Note:**
- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
 - Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.
 - (*) Properties obtained from film produced on a pilot line at TPE, Film thickness 12 micron, BUR 5:1, MD = Machine Direction, TD = Transverse Direction.



Technical Data Sheet	Product Name SCGC™ HDPE
Product Type High Density Polyethylene	Product Grade F15

Processing Guidelines

The actual extrusion condition depends on type of using machine, size and film thickness of product required. Generally, Melt temperature should be 180 °C-200 °C with blow up ratio (BUR) = 3-5 times and frost line height (FLH) = 8-10 times of die diameter

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical service at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.



Technical Data Sheet	Product Name SCGC™ HDPE
Product Type High Density Polyethylene	Product Grade F15

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Safety Data Sheet.
 - Declaration of Compliance.

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials