



Technical Datasheet

Product Name

SCGC PE WAX

Product Type

Non-Refined Polyethylene Homopolymer Wax

Product Grade

LP0040P

Product Description

LP0040P is a non-refined polyethylene homopolymer wax derived from the unique HDPE process by Thai Polyethylene Co., Ltd., a subsidiary of SCG Chemicals Co., Ltd. Under the careful control to ensure consistent product quality, LP0040P is guaranteed its high quality for various applications.

Typical Application

- Hot melt adhesive
- PVC compound
- Color masterbatch
- Thermoplastic road marking
- Plastic additive
- Petroleum wax blend
- Rubber
- Cable filling compound
- Candle

Product Characteristics

- High melting and softening point
- Low to medium viscosity
- Good heat resistance and thermal stability
- Excellent chemical resistance
- Excellent compatibility with other waxes
- Excellent lubrication

International Compliance

- Directive 2002/95/EC (RoHS) and Directive 2011/65/EU (RoHS Recast)
- Regulation (EC) No.1907/2006 (REACH)
- Directive 94/62/EC (Packaging and Packaging Waste)

Physical Properties

Property	Test Method	Typical Value	Unit
Viscosity @ 149 °C	ASTM D3236	20-40	cPs
Density	ASTM D1505	0.92	g/cm ³
Penetration Hardness	ASTM D1321	4	d.mm
Dropping Point	ASTM D3954	113	°C

Note: the given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



Technical Datasheet

Product Name

SCGC PE WAX

Product Type

Non-Refined Polyethylene Homopolymer Wax

Product Grade

LP0040P

Processing Guidelines

The recommended melt temperature is 130 - 150 °C. It is recommended to use mixing machine giving good homogenization. The recommend dosage depends on the intended applications which are shown below:

Applications	Recommendation
Hot melt adhesive	20 - 30% is recommended to reduce viscosity and adjust setting time of polyolefins, EVA base.
PVC compound	0.5 - 1.5 phr is recommended to be external lubricant for rigid PVC.
Color masterbatch	5 - 30% is recommended to improve pigment dispersion in polyolefins bases.
Thermoplastic road marking	1 - 3% is recommended to reduce viscosity for hydrocarbon resin base.
Plastic additive	5 - 8% is recommended to improve filler dispersion in polyolefins bases.
Petroleum wax blend	3 - 5% is recommended to add into a paraffin wax to increase softening point and hardness.
Rubber	2 - 10% is recommended to improve processability and additives dispersion.
Cable filling compound	5 - 10 phr is recommended to improve moisture barrier property.
Candle	1 - 5% is recommended to improve gloss, hardness and prolong candle life.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical services at the address as specified below.

Product Packaging

- White powder

Product Characteristics

- 20 kg loose bag
- 20 kg bag on pallet (pelletized wrap)

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.



Technical Datasheet	Product Name SCGC PE WAX
Product Type Non-Refined Polyethylene Homopolymer Wax	Product Grade LP0040P

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your technical services.

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Datasheet
 - Declaration of Compliance

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.